

PRODUCT DATA SHEET

| | | | |
|--|-------------------------------|----------------|----------------|
| ITEM: | DUNE ADAGGIO GOLD RECTIFICADO | BRAND: | BALDOCER, S.A. |
| DATE: | 29/04/2021 | FORMAT: | 30X60 cm |
| CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411) | | GROUP: | BIII |
| | | ANNEX: | L |

FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

| | UNE-EN-ISO-10545-2 | REFERENCE | RESULT |
|---------------------------|--------------------|-----------------|----------------------------|
| DIMENSIONS | | | 300X600 |
| LENGTH | | ± 0,5 % | 0,03% / -0,05% 599,8 mm |
| WIDTH | | ± 0,5 % | 0,03% / -0,02% 300,0 mm |
| STRAIGHTNESS OF SIDES | | ± 0,3 % | 0,03% / -0,03% |
| THICKNESS | | ± 10,0 % | 1,94% / -0,97% 9,0 mm |
| RECTANGULARITY | | ± 0,5 % | 0,10% / -0,12% |
| CENTRAL SURFACE FLATNESS | | +0,5 % / -0,3 % | 0,07% |
| LATERAL SURFACE FLATNESS | | +0,5 % / -0,3 % | 0,05% / -0,07% |
| DIAGONAL SURFACE FLATNESS | | ± 0,5 % | 0,09% / -0,04% |

PHYSICAL PROPERTIES

| | UNE-EN-ISO-10545-3 | | |
|---|--------------------|--------------------------|-----------|
| WATER ABSORPTION | | E > 10,0% | 14% |
| | UNE-EN-ISO-10545-4 | | |
| BREAKING STRENGTH | | MIN 600 N | 1150 |
| MODULUS OF RUPTURE | | MIN 12 N/mm ² | 20,2 |
| | UNE-EN-ISO-10545-6 | | |
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION | | NOT APPLY | NOT APPLY |
| | UNE-EN-ISO-10545-7 | | |
| DETERMINATION TO ABRASION RESISTANCE | | REVOLUTIONS | PEI |
| | | --- | --- |
| | UNE-EN-ISO-10545-9 | | |
| THERMAL SHOCK RESISTANCE | | | FULFILLED |

BALDOCER

UNE-EN-ISO-10545-11

| | | |
|--------------------|--|-----------|
| CRAZING RESISTANCE | | FULFILLED |
|--------------------|--|-----------|

UNE-EN-ISO-10545-12

| | | |
|------------------|--|---------------|
| FROST RESISTANCE | | NOT FULFILLED |
|------------------|--|---------------|

UNE 67101

| | | |
|--|--|---|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS | | 4 |
|--|--|---|

DETERMINATION OF SLIDING RESISTANCE

| | | |
|--|-------|-----|
| VALUE FOLLOWING UNE 41901-EX (PENDULUM) | CLASS | --- |
| VALUE FOLLOWING DIN 51130 (RAMP TEST) | R | --- |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS | --- |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E) | | --- |

CHEMICAL PROPERTIES

UNE-EN-ISO-10545-13

| | | |
|--|--|-----------|
| CHEMICAL RESISTANCE | | FULFILLED |
| HOUSEHOLD CHEMICALS | | GA |
| SWIMMING POOL SALTS | | GA |
| HYDROCHLORIC LOW CONCENTRATION | | GLA |
| CITRIC ACID | | GLA |
| POTASSIUM HYDROXIDE LOW CONCENTRATION | | GLA |
| HYDROCHLORIC HIGH CONCENTRATION | | GHA |
| LACTIC ACID | | GHA |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION | | GHA |

UNE-EN-ISO-10545-14

| | | |
|-------------------------|--|-----------|
| RESISTANCE TO STAINS | | FULFILLED |
| IRON OXIDE-CHROME OXIDE | | 5 |
| IODINE | | 5 |
| OLIVE OIL | | 5 |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

BALDOCER, S.A.
Ctra. La Pobla Tornesa - V. d'Alba, Km. 4
Tel: 902 456 700 - Fax 964 330 033
12192 VILAFAMÉS (Castellón)